
Description:	HEMPEL'S TEAK COLOUR RESTORER 67462 is a pigmented teak oil containing anti-mould agents to prevent discolouration. The wood obtains a golden brown colour after application.
Recommended use:	For use on new wood as well as on previously treated wood, interior and exterior, above the waterline.
Availability:	Part of European Yacht assortment. Local availability subject to confirmation.
PHYSICAL CONSTANTS:	
Shade nos/Colours:	65220/ Teak
Finish:	Transparent, Brown.
Volume solids, %:	38 ± 1
Theoretical spreading rate:	10 - 20 m ² /l [401 - 802 sq.ft./US gallon] depending on porosity
Flash point:	62 °C [143.6 °F]
Specific gravity:	0.9 kg/litre [7.3 lbs/US gallon]
Dry to touch:	1 hour 20°C/68°F 2 hour(s) 10°C/50°F
VOC content:	515 g/l [4.3 lbs/US gallon]
Shelf life:	5 years 25°C/77°F
	<i>The physical constants stated are nominal data according to the HEMPEL Group's approved formulas.</i>
APPLICATION DETAILS:	
Application method:	Brush / Roller
Thinner (max.vol.):	Do not dilute.
Cleaning of tools:	HEMPEL'S THINNER 808 (No 3) 08081
Indicated film thickness, dry:	Not relevant
Indicated film thickness, wet:	Not relevant
Safety:	Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult HEMPEL Safety Data Sheets and follow all local or national safety regulations.

SURFACE PREPARATION:	Preparation: Always ensure all surfaces are clean, oil free and dry. Clean with suitable detergent. Rinse the surface with fresh water. Allow to dry.. New wood: Sand and remove all dust. Saturate the dry, clean surface with suitable wood treatment, allow to dry. New teak: Clean with HEMPEL'S TEAK CLEANER 67543. Previously treated wood: Remove dust and loose material. Treat any bare spots with suitable wood treatment (not teak).
PRODUCT APPLICATION:	Method: Apply two coats of the product on internal areas and three coats on weather exposed areas. Previously treated wood: Apply 1-2 coats of the product. The product can be mixed 1:1 with a suitable wood treatment to aid penetration into the wood. It can be used on teak decks and other wood surfaces exposed to hard wear and tear ONLY if it is overcoated with HEMPEL'S TEAK OIL 67571.
APPLICATION CONDITIONS :	The surface must be completely clean and dry at the time of application and its temperature must be above the dew point to avoid condensation. The moisture content in the wood should not exceed: 16%. Do not apply in direct sunlight. In confined spaces provide adequate ventilation during application and drying.
RECOMMENDED DETERGENT :	HEMPEL'S PRE-CLEAN 67602
PRECEDING COAT:	HEMPEL'S TEAK CLEANER 67543, HEMPEL'S WOOD IMPREG 02362
SUBSEQUENT COAT:	HEMPEL'S TEAK OIL 67571 - on decks or hard-wear areas.
REMARKS:	Spillage, remaining oil, discarded cloths and similar should be discarded in a fireproof container due to the risk of auto ignition.
Stirring:	Stir product well before use..
Storage Conditions:	Exposure to air and temperature variances should be avoided. Avoid direct sunlight. Keep containers tightly sealed. Store at temperatures: 5°C/41°F - 35°C/95°F.
Overcoating:	Not relevant
Note:	HEMPEL'S TEAK COLOUR RESTORER 67462
ISSUED BY:	HEMPEL A/S 6746265220

This Product Data Sheet supersedes those previously issued.

For explanations, definitions and scope, see "Explanatory Notes" available on www.hempel.com. Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.

The Products are supplied and all technical assistance is given subject to HEMPEL's GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice and become void five years from the date of issue.